DERWENT-ACC-NO: 1976-06826X

DERWENT-WEEK: 197604

COPYRIGHT 1999 DERWENT INFORMATION LTD

TITLE: More conductive coating for cathodic emitters - by addn.

of metal oxides to alkaline earth metal carbonates

PATENT-ASSIGNEE: MERKUSHEV O M[MERKI]

PRIORITY-DATA: 1972SU-1815986 (July 28, 1972)

PATENT-FAMILY:

PUB-NO PUB-DATE LANGUAGE PAGES MAIN-IPC

SU 425240 A February 19, 1975 N/A 000 N/A

INT-CL (IPC): H01J009/04

ABSTRACTED-PUB-NO: SU 425240A

BASIC-ABSTRACT:

Title coatings, which may be usd in gas-discharge apparatus etc. have high cohesive and adhesive props and are prepd. from proposed suspn. of compsn. (pbw): alkaline earth metal e.g. Ca, Sr, Ba carbonate 30-59.9; metal oxide (gp IV and/or gp. III-VIII metal higher oxides) 30.0-0.7; hydroxyethylcellulose (binder) 0.1-2; water 39.9-38, which gives strong, dense and even coatings. In an example, the proposed suspn. is ball-milled 10-40 hrs. before applying by usual methods (e.g. pouring, electrophoresis, sedimentation etc) to the cathode and heating to form salts, e.g. titanates, vanadates, chromates etc.

TITLE-TERMS: MORE CONDUCTING COATING CATHODE EMITTER ADD METAL ALKALINE EARTH METAL

DERWENT-CLASS: A85 G02 L03 V05

CPI-CODES: A03-A04A; A12-E; G02-A05; L03-C02A;

POLYMER-MULTIPUNCH-CODES-AND-KEY-SERIALS:

Multipunch Codes: 012 04-23& 231 236 240 252 359 431 477 609 623 627 722 726